

Polyurethane Rebond

Suitable for stretch-fit installation of carpets

End Use Classification (BS 5808: 1991): L/U, Luxury Use

Roll Area: 15.07m² (1.37m x 11.0m) *

Specification	BS Requirements	Result	Method
Nominal square weight		1049 g/m ²	
Nominal density		98kg/m ³	
Nominal roll weight		34.9 lbs	
Nominal thickness		10.00 mm	BS 4051
Mean original thickness from nominal thickness	Maximum 12%	0.17%	
Difference between max. & min. original thicknesses	Maximum 3mm	0.36mm	
Work of compression	Minimum 50 J/m ² after dynamic loading for 1000 impacts	165 J/m ²	BS 4098 & BS 4052
Compression after dynamic loading	Minimum 2mm, maximum 7mm after 1000 impacts	6.6mm	
Retention of work of compression	Minimum 40% of original after 1000 impacts	86.3%	
Breaking strength - length	Minimum 40N	92 N	BS 2576
Breaking strength - width		50 N	
Extension under force - length	Maximum 10% @ 40N	6.4%	
Extension under force - width		38.9%	
Loss in thickness after dynamic loading	Maximum 15% after 1000 impacts	1.8 %	BS 4052
Loss in thickness after static loading	Maximum 15% after 24hrs loading & recovery	1.0 %	BS 4939
Resistance to cracking	Not greater than 50mm	Pass	BS 5808
Odour		No objectionable odour	
Colour / backing		Orange / nonwoven backing	
Flammability	Notes	Result	Method
Hot metal nut test	Tested in Interfloor laboratory	Low radius of effects of ignition	BS 4790 & BS 5287
Thermal Properties			
Thermal resistance		2.64 Tog	BS 4745
Acoustic Properties			
Weighted reduction in impact sound pressure level (Delta Lw)		39 dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997

Item Code TAZEST

Issue No. 5

Issue Date 19-Nov-09

Page No. 1 of 1

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted.

This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

Interfloor Ltd., Broadway, Haslingden, Rossendale, Lancashire, BB4 4LS.

Tel: +44(0)1706 213131 Fax: +44(0)1706 260800 Web: www.interfloor.com

International Enquiries: Telephone: +44(0)1706 238824 Fax: +44(0)1706 225114